

**Viking BUR Restore rejuvenates aged asphalt flood coats and restores many of their original properties. Its even blend of premium oxidized asphalt and penetrating oils, alongside quality non-asbestos reinforcing fillers, provides rejuvenating qualities to worn down asphalt BUR systems. Viking BUR Restore eliminates the use of kettles and open flames and meets current Volatile Organic Compound (VOC) regulations.**

### FEATURES & BENEFITS

- Resaturates weathered and exposed roofing felts and fabrics
- Rejuvenates aged asphalt flood coats
- Extends the life of the roofing system by resealing cracks and other imperfections in the flood coat

### PACKAGING

Viking BUR Restore is available in 5-gallon pails. It is black in color.

### STORAGE & HANDLING

Store Viking BUR Restore in a cool, dry, and ventilated place. Keep container closed when not in use. Store locked up.

### APPLICATION

All surfaces must be clean, free of heavy dirt, dust, debris, oils, loose gravel, un-adhered coatings, scaling rust, deteriorated membranes, and other contaminants that may result in a surface that is not sound. Surface must be free of frost, snow, and ice. Aggregate may need to be spud away to provide a proper work surface. Fasteners must be repaired and/or replaced, as needed. If a primer is required, BITEC Asphalt Primer 41 is recommended.

Viking BUR Restore is ready to apply from the bucket. Cold apply by brush, squeegee, or airless spray equipment at a rate of 4-8 gallons per 100 ft<sup>2</sup>. Re-embed gravel where applicable.

### PRECAUTIONS

Viking BUR Restore is for exterior use only and should not be thinned. Do not use this product where it may come into contact with potable water. Do not apply to damp or wet surfaces. Do not use on or with products containing coal tar pitch. Do not use on or with rubber or plastic substrates.

Safety first! The roofing contractor and employees are the key to success regarding safety. Safety should always be first! Read all label information, SDS, and precautions before using. For safety information on our products, please visit [www.bitec.com](http://www.bitec.com).

Technical Schedule	
Coverage Rate	4 - 8 gal / 100 ft <sup>2</sup>
Viscosity, grams (Stormer @ 200 rpm)	700 - 1100
Total Solids (D6511) % by weight	75 - 80
Total Solids % by volume	70 - 75
Flash Point (PMCC)	105°F (40.6°C)
Color	Black
Drying Time, Touch @ 70°F (21.1°C) / 50% R.H.	1 hour
Shelf Life @ 70°F (21.1°C) / 50% R.H.	1 year
VOC (EPA Method 24A)	<300 g / L
Weight (ASTM D6511)	8.5 - 9.0 lbs / gal

*All information is given in good faith but normal tolerances of manufacture and testing will apply. BITEC reserves the right to improve and change its products at any time without prior notice or advice. The use of BITEC products is determined by local conditions and individual requirements of each contract. In consideration of the many factors involved, BITEC cannot be held responsible for the improper application of its products and for conditions beyond its control. All claims filed against BITEC warranties will be subject to the provisions set forth at the date of the warranty issuance, and any addendum thereto. Under no circumstances will BITEC be held liable for any damage, whether personal injury or property damage, which occur during or after the application of any BITEC products.*

